

Texylon Stick

Code A31159865001

PRODUCT DESCRIPTION

Solvent based polyurethanic adhesive.

APPLICATION FIELDS

Adhesive for the realization of solvent based transfers.

APPLICATION PROCESS

Substrate	100% COTTON, COTTON MIXED WITH SYNTHETIC FIBERS, ELASTIC SUBSTRATES. SUBSTRATES MAY BE WHITE OR COLOURED.
Th/Cm	From 32 to 55 th/cm
Emulsion	See the product range table
Squeegee	Square edge Squeegee hardness: 60-65 Shores
Transfer	180°C for 10-15 seconds
Thinners	Thinner 90.904 Rapid Thinner 90.924 Normal Thinner 90.918 Slow
Cleaning	Solvent LQ 90.920
Storage	If kept in its original sealed package, the product has a shelflife of 2 years.
Packaging	1 kg
Safety data sheet	Available upon request

WARNING

This technical data sheet does not replace either the Safety Data Sheet or the specific Conformity Declaration. These documents may be required to our SHEQ (Product safety office), at the following e-mail address: safety@eptainks.com

The technical data sheet does not relieve the printer, who remains the only responsible of the respect of the regulations, the specifications and the related required certifications of the finished items.

GENERAL FEATURES

- Good elasticity
- After transferring, the prints resist water washing at 40°C.

PREPARATION

Before using, the ink must be well mixed and, in case, diluted according to the printing requirements.

TECHNICAL FEATURES

The performance of the product, printed with a 43 Th/cm screen, is 18-20 m²/kg. These data are merely an indication, since they depend on the dilution, the substrate and the printing equipment.

SPECIAL RECOMMENDATIONS

- Always test the characteristics of the product, before starting production.
- The above information is the result of previous knowledge and experience; do not represent guarantee or insurance.
- This adhesive does not resist dry clearing and bleaching.

IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us of the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.